

Lawton Adams Construction Co.
260 Route 100 Somers, NY 10589
(914) 232-3275

Sieve Analysis Report

09/08/2026

1300-Subbase (Fine-3/4")				
Procedure	Sieve/Test	Average	Unit	NYS DOT Subbase Type 2
	4" (100mm)	100	%	100-100
	3" (75mm)	100	%	
	2" (50mm)	100	%	
	1 1/2" (37.5mm)	100	%	
	1" (25mm)	98	%	
	3/4" (19mm)	84	%	25-60
	1/2" (12.5mm)	66	%	
	3/8" (9.5mm)	56	%	
	1/4" (6.3mm)	52	%	
	#4 (4.75mm)	50	%	
	1/8" (3.17mm)	44	%	5-40
	#10 (2mm)	40	%	
	#20 (.85mm)	26	%	
	#40 (.425mm)	20	%	
	#80 (.18mm)	14	%	
	#200 (75µm)	7.4	%	0-10

Signature	
Name/Title	Michael Crowley / Regional Quality Control Manager